

Planning documents Waterproofing system for waterproof-concrete joints Triflex JWS



Applications



The waterproof-concrete construction method has been used in a range of practical applications for decades. In addition to underground car parks, waterproof-concrete is also used to build roofs and components that are in contact with soil – often including subsequent greening. Although this construction method has proven effective, damage still often occurs at recurring weak points, particularly at the construction and settlement joints of the individual components and at penetrations.

Triflex JWS is a fleece-reinforced waterproofing system for concrete joints, and is used specifically in new builds and in the refurbishment of white tanks. The system design, consisting of high-quality PMMA resins, is resistant to hydrolysis as well as roots and rhizomes in accordance with FLL guidelines. It can also be used in areas in contact with the soil.

Triflex has almost 40 years experience of using durable liquid-applied waterproofing and coating systems in the world of building refurbishment. Triflex JWS is a system solution specially developed for waterproofing work on white tanks, and has a General Building Supervisory Authority Test Certificate.

Secure joints for complex geometries

White tanks require that simple, monolithic constructions are chosen, however if this design is not to the client's taste, installing joint tapes correctly can often prove difficult. if further complex construction then takes place on top of the substructure, the watertightness of the joints must be guaranteed long term.

Thanks to the liquid waterproofing application, reliable protection is ensured down to the smallest detail, allowing for the uniform waterproofing of all types of details and joints, whether in compact spaces or in unusual configurations. The full-surface substrate adhesion also prevents underflow beneath the waterproofing.





Advantages at a glance

Waterproof down to the smallest detail

The cured resin forms a seamless and joint-free surface. Even complicated details such as door sills and cross joints can be easily and homogeneously waterproofed using liquid application techniques.

Short processing times

The liquid-applied Triflex JWS system has particularly rapid curing times. The primer and waterproofing resins can be recoated after just 45 minutes and the system is resistant immediately after full installation has been completed.

Durable system design

Triflex JWS has excellent mechanical and chemical stability. The system is hydrolysis and alkali resistant. The systems full-surface bond with the substrate means there is no underflow beneath the waterproofing. Faulty joint tapes can be easily waterproofed from the top sides in refurbishment projects.

Suitable for use in new builds and refurbishments

The waterproofing and protective layer are combined to create one single system. The low build-up height of just a few millimetres means that no special structures need to be developed for the construction. The material simply adapts to the contours like a second skin.

Certified safety

The Triflex ProDetail/ProTect waterproofing resins used in the Triflex JWS system have a General Building Supervisory Authority Test Certificate (abP) in accordance with the Building Regulations List A, Part 2, No. 1.4 – Normally flammable joint waterproofing for concrete components with high waterpenetration resistance against pressurised and non-pressurised water and against ground moisture. The tests are based on the testing principles for joint waterproofing (PG-ÜBB): The junctions of structural waterproofing on concrete components with high penetration resistance and in accordance with the specifications in the working group Building Regulations List A, Part 2, No. 1.4 on the assessment of settlement joints. The system is also root and rhizomeresistant in accordance with FLL specifications, and is suitable for use in water-exchange zones in usage class A, wear classes 1 and 2 in accordance with the German Directive on Watertight Concrete Structures (WU Directive).

And this is how it's done ...



1. The concrete substrate is ground in order to remove the cement slurry.



2. Joint areas are primed with Triflex Cryl Primer 276.



3. The fitted PE round sealing band is taped with Triflex duct tape.



4. The Triflex ProDetail waterproofing resin is decanted ...



5. ... and mixed with Triflex Catalyst.



6. A sufficient amount of Triflex ProDetail is applied, ...



7. ...the Triflex Special Fleece is laid, ensuring that there are no air bubbles ...



8. ... and covered wet-on-wet with Triflex ProDetail.



9. A protective later of Triflex ProDetail is then applied.



10. After three hours, further construction can be carried out on a protective mat.





Compatible system components

All the Triflex products mentioned in this system are lab-scale and application coordinated as a result of years of experience. This standard of quality ensures optimum results during both application and use.



System description

Properties

- Fully reinforced waterproofing system with a polymethyl methacrylate (PMMA) base for waterproofing construction, controlled crack, expansion and settlement joints on waterproof-concrete components.
- Hydrolysis-resistant
- Seamless
- Cold-applied
- Fast-curing
- Flexible in low temperatures
- Excellent adhesion properties on a multitude of substrates
- Root and rhizome-resistant in accordance with FLL specifications
- Extremely weather-resistant (UV, IR, etc.)
- Elastomeric and crack-bridging
- Joint waterproofing on the side facing the water
- Vapour-permeable
- · Resistant to all chemicals naturally present in soil and rainwater

- Resistant to sparks and radiant heat (DIN 4102)
- ETA certification with CE marking
- General Building Supervisory Authority Test Certificate (AbP) in accordance with the Building Regulations List A, Part 2, No. 1.4 – Normally flammable joint waterproofing for concrete components with high water-penetration resistance against pressurised and non-pressurised water and against ground moisture. The tests are based on the testing principles for joint waterproofing (PG-ÜBB): The junctions of structural waterproofing on concrete components with high penetration resistance and in accordance with the specifications in the working group Building Regulations List A, Part 2, No. 1.4 on the assessment of settlement joints.
- The waterproofing system is suitable for use in water-exchange zones in usage class A, load classes 1 and 2 in accordance with the German Directive on Watertight Concrete Structures (WU Directive).

Determination of construction type

	Triflex JWS, version 1	Triflex JWS, version 2
Joint type	Controlled crack joint, construction joint, settlement joint	Settlement joint
Joint width	< 30 mm	≥ 30 mm
Max. resulting deformation	D _r = 22,4 mm *	D _r = 26,9 mm *
Max. water pressure	Permissible: 0.3 bar / 3 m water column Tested: 1.5 bar / 15 m water column	Permissible: 0.4 bar / 4 m water column Tested: 2.0 bar / 20 m water column

* With max. resulting deformations, the test setups and their results must be observed based on the associated General Building Supervisory Authority Test Certificate (AbP). These form the basis of the values reached. Changes to the geometry, the uncoupling zones and the loop depths can cause the max. resulting deformation values to be higher or lower.

Triflex JWS, version 1

Triflex JWS, version 2





System description

System design

Primer

Triflex Primer for sealing the substrate and ensuring substrate adhesion.

Duct tape

Triflex duct tape for defining the gap created by the joint.

Joint waterproofing

Triflex waterproofing membrane, fully reinforced with a polyester Triflex Special Fleece.

Protective layer

Waterproof protective layer.

Substrate

Substrate suitability should always be checked on a case by case basis. The substrate must be clean, dry and free of cement bloom, dust, oil, grease and other adhesion-reducing dirt.

Moisture: When carrying out coating work, the substrate moisture must not exceed 6 % by weight. Ensure that structural measures are taken to prevent moisture penetration of the coating from underneath.

Dew point: During application, the surface temperature must be at least $3 \,^{\circ}$ C above the dew point temperature. Below this temperature, a separating film of moisture can form on the surface.

Hardness: Mineral substrates must be permitted to fully harden for at least 28 days.

Adhesion: The following tensile strengths must be verified on pre-treated test surfaces: Concrete, in the centre, at least 1.5 N/mm², individual value not less than 1.0 N/mm².

Substrate pre-treatment

Substrate	Vorbehandlung	Grundierung
Aluminium ⁽¹⁾	Abrade with Triflex Cleaner, roughen surface	No primer ⁽²⁾
Asphalt	Grinding, milling or dust-free shot-blasting	Triflex Cryl Primer 222
Composite thermal insulation systems ⁽¹⁾	Remove any loose objects	Triflex Pox R 100
Concrete	Grinding, milling or dust-free shot-blasting	Triflex Cryl Primer 276
Copper ⁽¹⁾	Abrade with Triflex Cleaner, roughen surface	No primer ⁽²⁾
EPDM waterproofing sheeting	Roughen surface, adhesive strength and compatibility test	Triflex Primer 610
Epoxy resin coating	Roughen surface, adhesive strength and compatibility test	No primer
FRP light shaft	Abrade with Triflex Cleaner, roughen surface	No primer
Glass ⁽¹⁾	Abrade with Triflex Glass Cleaner, adhesive strength test	Triflex Glass Primer
Hot bitumen coating	Adhesive strength test	Triflex Cryl Primer 222
Mortar, resin-modified	Grinding or dust-free shot-blasting; adhesive strength and compatibility test	Triflex Pox R 100
Paints	Completely grind off	See substrate
Plaster/masonry ⁽¹⁾	Roughen surface	Triflex Cryl Primer 276
Polymer bitumen sheeting (PY-E) mod. (SBS)		No primer
Polymer bitumen sheeting (PY-P) mod. (APP)	Adhesive strength test	Triflex Cryl Primer 222
PU coating	Roughen surface, adhesive strength and compatibility test	No primer
PVC moulded components, hard ⁽¹⁾	Abrade with Triflex Cleaner, roughen surface	No primer
Screeds	Grinding or dust-free shot-blasting	Triflex Cryl Primer 276
Stainless steel ⁽¹⁾	Abrade with Triflex Cleaner, roughen surface	No primer ⁽²⁾
Steel, galvanised	Abrade with Triflex Cleaner, roughen surface	No primer ⁽²⁾
Tiles	Completely remove	Triflex Cryl Primer 276
Wood ⁽¹⁾	Completely remove	Triflex Cryl Primer 276
Zinc ⁽¹⁾	Abrade with Triflex Cleaner, roughen surface	No primer ⁽²⁾

⁽¹⁾Only in areas not subject to high mechanical stress, e.g., details and flashing.

(2) Alternative to roughening: Abrade with Triflex Cleaner, prime with Triflex Metal Primer. Loose rust and blistering rust must first be removed. Information on other substrates is available on request.

.....

Important note:

Adhesion to the substrate must be checked on a case-by-case basis!

System description

Primer

Triflex Cryl Primer 222

Apply evenly with a Triflex universal roller. Volume: at least 0.40 kg/m². Can be recoated after approx. 45 min.

Triflex Cryl Primer 276

Apply evenly with a Triflex universal roller. Volume: at least 0.40 kg/m². Can be recoated after approx. 45 min.

Triflex Glas Primer

Wipe on GP evenly with a cleaning cloth. Volume: approx. 50 ml/m². Can be recoated after approx. 15 min up to max. 3 hrs.

Triflex Metal Primer

Spray a thin coat with a spray can, or apply thinly with a short-pile roller. Volume: approx. 80 ml/m². Can be recoated after approx. 30 to 60 min.

Triflex Pox R 100

Apply evenly using a Triflex universal roller and immediately sand down with plenty of quartz sand. Volume of Triflex Pox R 100 at least 0.30 kg/m², volume of quartz sand 0.2–0.6 mm at least 2.00 kg/m². Can be recoated after approx. 12 hrs.

Triflex Primer 610

Apply evenly with a brush or roller. Volume: approx. 40 to 80 g/m². Can be recoated after approx. 20 min.

Important note:

The primer should be added approx. 2 cm above the area to be waterproofed in order to prevent water ingress in the transition area. This means that the primer is visible on both sides along the entire length.

Repairing

Triflex Cryl Paste

For filling in shrinkage cracks, smaller areas of damage and unevenness. Volume: at least 1.40 kg/m² per mm layer thickness. Can be recoated after approx. 1 hr.

Triflex Cryl RS 240

For levelling large areas of damage. Volume: at least 2.20 kg/m² per mm layer thickness. Can be recoated after approx. 45 min.

Joint waterproofing, version 1

Controlled crack joint, construction joint, settlement joint:

1. PE round sealing band

Fit a closed-cell PE round sealing band (d = joint width +25 %) if necessary in order to seal the joint.

2. Triflex Cryl Paste

Insert correctly into the joint. Volume: approx. 1.40 kg/m² per mm layer thickness. Can be recoated after approx. 1 hr.

3. Triflex duct tape

Attach to the center of the joint to cover the gap. Width 10 cm. The subsequent application is wet-on-wet:

4. Triflex ProTect/Triflex ProDetail

Apply a width of 35 cm with a radiator roller. Volume: at least 0.70 kg/m.

5. Triflex Special Fleece

Lay a 35 cm wide fleece strip, removing any air bubbles. Overlap the ends of the fleece strip by at least 5 cm.

6. Triflex ProTect/Triflex ProDetail

Apply until the Triflex Special Fleece is fully saturated. Volume: at least 0.35 kg/m. Can be recoated after approx. 45 min.

Joint waterproofing protective layer:

7. Triflex ProTect/Triflex ProDetail

Apply as a protective layer. Volume: at least 0.55 kg/m. Total volume of Triflex ProTect/Triflex ProDetail: at least 1.60 kg/m. Resistant after approx. 3 hrs.

For dimensions, see Triflex JWS system drawings.

Important note:

- Triflex ProDetail is recommended for vertical areas. Other areas should be waterproofed by adding Triflex Liquid Thixo to Triflex ProTect at a maximum of 1 wt. % to create a thixotropic finish.
- The fleece widths should be determined based on requirements. A fleece reinforcement junction of at least 10 cm should be used on the components. It may be necessary to work with two different fleece widths.

System description

Joint waterproofing, version 2

Settlement joint:

1. Triflex Cryl Paste

Apply a width of approx. 4 cm to both sides of the joint to bond the Triflex Support Strip.

2. Triflex Support Strip

Lay in the joint as a loop. There must be a loop depth of at least 2 cm. Can be recoated after approx. 1 hr.

The subsequent application is wet-on-wet:

 Triflex ProTect/Triflex ProDetail
 Apply to both sides of the joint and on the support strip
 using a radiator roller.
 Volume: at least 0.70 kg/m.

4. Triflex Special Fleece

Insert a 35 cm wide fleece strip as a loop, making sure there are no air bubbles. There must be a connection width of at least 10 cm. In corner areas, the Triflex Special Fleece for inner and outer corners must be used.

5. Triflex ProTect/Triflex ProDetail

Apply until the Triflex Special Fleece is fully saturated. Volume: at least 0.40 kg/m.

Can be recoated after approx. 45 min.

Total volume of Triflex ProTect/Triflex ProDetail: at least 1.10 kg/m.

6. PE round sealing band, closed-cell Place in the joint; see system drawing.

7. Triflex ProTect/Triflex ProDetail/Triflex Cryl Paste Fill or seal the joint so it is flush with the surface. Volume approx. 2.20 kg/m pro mm layer thickness. Can be recoated after approx. 45 min.

8. Triflex duct tape

Attach to the center of the joint to cover the gap. Joint width $(1 \times 10 \text{ cm or } 2 \times 5 \text{ cm duct tape})$

The subsequent application is wet-on-wet.

9. Triflex ProTect/Triflex ProDetail

Apply a width of 36 cm with a radiator roller. Volume: at least 0.70 kg/m.

10.Triflex Special Fleece

Lay a 35 cm wide fleece strip, removing any air bubbles. Overlap the ends of the fleece strip by at least 5 cm.

11.Triflex ProTect/Triflex ProDetail

Apply until the Triflex Special Fleece is fully saturated. Volume: at least 0.40 kg/m.

Joint waterproofing protective layer.

12.Triflex ProTect/Triflex ProDetail

Apply with a radiator roller.

Volume: at least 0.55 kg/m.

Total volume of Triflex ProTect/Triflex ProDetail: at least 1.65 kg/m

(without joint filling).

Resistant after approx. 3 hrs.

For dimensions, see Triflex JWS system drawings.

Important note:

Triflex ProDetail is recommended for vertical areas. Other areas should be waterproofed by adding Triflex Liquid Thixo to Triflex ProTect at a maximum of 1 wt. % to create a thixotropic finish.

Protective measures

It is recommended that the waterproofing membrane is protected against mechanical damage in the event of subsequent work or build-ups. This can be provided with a protective fleece or a loosely laid protective mat.

Finishing

The system does not require finishing. Details can be finished for aesthetic purposes.

Triflex Cryl Finish 205

Cross-coat evenly using a Triflex universal roller. Volume: at least 0.50 kg/m². Rainproof after approx. 30 min.

What to do if work is interrupted

If work is interrupted for more than 12 hrs, or if soiled by rain etc., clean with Triflex Cleaner allowing 20 min. airing time. Airing time at least 20 min. Transitions to subsequent waterproofing must overlap (including Triflex Special Fleece) by a minimum of 10 cm. This also applies to junctions, transitions and detail solutions with Triflex ProDetail. The finish must be applied within 24 hrs. If this application is delayed for any reason, the surface to be finished must be pre-treated with Triflex Cleaner.

System components

For information on applications, conditions for use and instructions for mixing, see product information (request if necessary):

Triflex Cleaner Triflex Cryl Finish 205 Triflex Cryl Paste Triflex Cryl Primer 222 Triflex Cryl Primer 276 Triflex Cryl RS 240 Triflex Glass Primer Triflex Glass Primer Triflex Liquid Thixo Triflex Metal Primer Triflex Pox R 100 Triflex Primer 610 Triflex ProDetail Triflex ProTect Triflex Special Fleece

System description

Quality standard

All Triflex products are manufactured in accordance with the standards defined in ISO 9001. To ensure quality is not compromised, Triflex products are only installed by specialist, fully trained and qualified contractors.

Gradient / Evennes

Before commencing any surfacing work and during the work itself, it is essential to ensure the correct gradient and evenness of the substrate. Any corrections required must be taken into account during this work.

Dimensional tolerances

When carrying out surfacing work, always ensure compliance with the permissible tolerances for building construction (DIN 18202, Table 3, line 4).

Safety tips / Accident prevention

Read the safety data sheets before using the products.

Volumes required / Waiting times

The specified volumes apply only to smooth, even surfaces. Special allowances must be made for unevenness, roughness and porosity. Information regarding airing and waiting times applies to a substrate at an ambient temperature of +20 °C.

General notes

The basis for the use of Triflex products can be found in the system descriptions, system drawings and product information sheets. It is essential to heed these when planning and carrying out the building project.

Departures from the technical information of Triflex GmbH & Co. KG applicable at the time of work can compromise the guarantee. Any project-related departures are subject to the written authorisation of Triflex.

All data is based on general regulations, directives and other technical rules. The general regulations applicable in the particular country of use must be respected.

Since the parameters can vary from case to case, the contractor is required to test the suitability of aspects such as the substrate.

Non-system substances must not be added to Triflex products. Subject to change in the interests of technical advancement or enhancement of Triflex products.

Tender texts

Please visit the Download section of the Triflex website at www.triflex.com to obtain the current standard specifications for tender, which are available in a range of different file formats.

CAD drawings

All CAD system drawings can be downloaded free of charge from the Download section of the Triflex website www.triflex.com.

System drawings



Height differences between fleece overlaps are exaggerated

System drawings





System design – Detail B Protective layer Triflex ProTect/Triflex ProDetail Triflex ProTect/Triflex ProDetail Joint waterproofing reinforced with Triflex Special Fleece Triflex ProTect/Triflex ProDetail Loop waterproofing reinforced with **Triflex Special Fleece** See substrate pre-treatment Primer Substrate





Test certificates

		Geschäftsbereich V - Tiefbau Prof. Dr. Ing. Olaf Selle beitsgruppe 6.1 - Bauwerkaabdichtung		
Allgeme	ines bauaufsichtliches	Prüfzeugnis		
Prüfzeugnis Nummer:	P-SAC 02 / 5.1 / 12 - 229-1			
Gegenstand:	Triffex JWS, Variante 1 - außenliegende Abdichtung von Br aus Beton mit hohem Wassereind Bauregelliste A, Teil 2, lfd. Nr. 1.4	ewegungsfugen für Bauteile Iringwiderstand gemäß , Ausgabe 2013/2		
Antragsteller:	Triflex GmbH & Co. KG Karlstraße 59 D 32423 Minden	MEDA	MEPA	Leipzia Grr
Ausstellungsdatum:	26.08.2013		Prüf, Überwa Baus	chungs- und Zertifizierungss toffe, Bauprodukte und Baus Geschäftsbereich V - Prof. Dring. C
Geltungsdauer:	25.08.2018		Arb	eitegruppe 5.1 - Bauworkaabo
Dieses allgemeine bauaufs	sichtliche Prüfzeugnis besteht aus 8 Si ne Prüfzeugnis darf nur ungekügst vervieifitigt	Allgemei	nes bauaufsichtliches F	Prüfzeugnis
Dieses algemeine bauaufs Dieses algemeine bauaufschtlic weise - bedarf der vorterigen als Solvitierum al Organaumenchrit Es geten die Algemeinen Gesch	sichtliche Prüfzeugnis besteht aus 8 S- Ihe Prüfzeugnis darf nur ungeküczt verwielltitig brifflichen Zustimmung der MFPA Leipzig Ge- einund Cognationnengel desider Zeinfnungsbe- aftabedingungen (AGB) der MFPA Leipzig Ger Dum es bindt Gest nun DV (14) 10015 Dum es bindt Gest nun DV (14) 10015	Allgemei Prützeugnis Nummer:	nes bauaufsichtliches F P-SAC 02/5.1/13-438	Prüfzeugnis
Dieses algemeine bauauft Dieses algemeine bauauftechtic weise – bedarf der untergen zu Schriftform mit Originalunterschri Es gelten die Algemeinen Gesch Keisen und Algemeinen Gesch Keisen und Algemeinen Gesch Keisen und Algemeinen Gesch	ischtliche Prüfzeugnis besteht aus 8 S- ne Prüfzeugnis daff nur ungeküszt verviellstig Mittlichen Zustimmung der MFPA Lepzig Gm affabedingungen (AGB) der MFPA Lepzig Gm Mittlichen zustimmen der stellter Zeitifnungste affabedingungen vordiniseren für aussi- mung ist eine ein den Orden auf der MFPA Lepzig Gm Konn aussisten vervielle aussistenten fürderfahren ist denson Delauent inf aussistenten fürderfahren ist delauen Delauent inf aussistenten fürderfahren ist eine Unsets aufgebreiten fürderfahren ist delauen Delauent inf aussistenten fürderfahren ist delauen Delauent inf aussistenten fürderfahren ist delauen Delauent inf aussistenten fürderfahren delauen delauent inf aussistenten fürderfahren delauent delauent inf aussistenten fürderfahren delauent delauent inf aussistenten fürderfahren delauent delauent informationen fürderfahren delauent delauent delauent informationen fürderfahren delauent delauent delauent delauent delauent fürderfahren delauent delauen	Allgemei Prützeugnis Nummer: Gegenstand:	P-SAC 02 / 5.1 / 13 - 438 P-SAC 02 / 5.1 / 13 - 438 Triffex JWS, Variante 2 - außanliegende Abdichtung von Be aus Baton mit hohem Wassereinde Bauregelitste A, Teil 2, lfd. Nr. 1.4,	Prüfzeugnis wegungsfugen für Bau ingwiderstand gemäß Ausgabe 2014/2
Dieses algemeine bauauft Dieses algemeine bauauftechtig weise – bedarf der untherigen as Schriftform mit Originalunterschrift Es gelten die Algemeinen Gesch weise weisen die Algemeinen Gesch Weise weisen die Algemeinen Gesch Weise weisen die Algemeinen Gesch	sichtliche Prüfzeugnis besteht aus 8 S- he Prüfzeugnis daf nur ungeküszt vervielläsig wittlichen Zustimmung der MFPA Lepzig Ge- hen und Organisatierspel deuter Zeichnungste affabedingungen (AGB) der MFPA Lepzig Ge- men so basis deuter and nur mit auferne höhertigen im deuter auch nur deuter deuter and höhertigen im deuter auch nur deuter deuter and höhertigen im deuter auch nur deuter deuter and höhertigen im deuter aufer and höhertigen im deuter aufer and höhertigen ein deuter aufer aufer aufer and höhertigen ein deuter aufer aufe	Allgemei Prüfzeugnis Nummer: Gegenstand: Antragsteller:	nes bauaufsichtliches F P-SAC 02 / 5.1 / 13 - 438 Triffex JWS, Variante 2 - außanliegende Abdichtung von Be aus Beton mit hohem Wassereind Bauregelitste A, Teil 2, lfd. Nr. 1.4, Triffex GmbH & Co. KG Karistraße 59 D 32423 Minden	Prüfzeugnis wegungsfugen für Beu ingwiderstand gemäß Ausgabe 2014/2
Dieses allgemeine bausufs Dieses allgemeine bausufuchtlich seisen - bedraf der vorherigen st Schriftom mit Originalunterschri Es geten die Allgemeinen Gesch weisen - bester die Allgemeinen Gesch Schriftom mit Originalunterschrift Es geten die Allgemeinen Gesch Schriftom die Allgemeinen die All	An Philippings And nor ungebied were Signature and Signatu	Allgemei Prützeugnis Nummer: Gegenstand: Antragsteller: Ausstellungedatum:	nes bauaufsichtliches F P-SAC 02 / 5.1 / 13 - 438 Triflex JWS, Variante 2 - außanliegende Abdichtung von Be aus Bauregelliste A, Teil 2, lfd. Nr. 1.4, Triflex GmbH & Co. KG Karlstraße 59 D 32423 Minden 12.01.2015	Prüfzeugnis wegungsfugen für Bau ingwiderstand permäß Ausgabe 2014/2
Dieses algemeine bausufaction beses algemeine bausufaction beses - bedarf der verbengen so Schriftom mit Organalunterschrift Es geten die Algemeinen Gesch Dieses Betranden Algemeinen Besch Dieses Betranden Algemeinen Besch Dieses Betranden Algemeinen Besch Betranden Besch Betranden Besch Betranden Besch Betranden Besch Betranden Besch Besch Besch Besch Besch Besch Bes	sichtliche Prüfzeugnis besteht aus 8 Sr he Prüfzeugnis daf nur ungekürzt vervielläig her und Organisterreit de Sider Zeichnungs antabedeingungen (AGB) der MFPA Leppi Gm Dum is Diels Gerst nun brit führt in der her und Organisterreit der Sider Zeichnungs der Sider Sider aus der Kim Bilder her und Des Sider aus der Kim Bilder her der Bilder aus der Kim Bilder her Bilder aus der Kim Bilder her Bilder aus der Kim Bilder her Bilder aus der Bilder her Bilder aus der Bilder her Bilder aus der Bilder her Bilder aus der Bilder her Bild	Allgemein Prüfzeugnis Nummer: Gegenstand: Antragsteller: Ausstellungsdatum: Geltungsdauer:	nes bauaufsichtliches F P-SAC 02 / 5.1 / 13 - 438 Triffex JWS, Variante 2 - außanliegende Abdichtung von Be aus Beton mit hohem Wassereind Bauregelliste A, Teil 2, tid. Nr. 1.4, Triffex GmbH & Co. KG Karistraße 59 D 32423 Minden 12.01.2015 11.01.2020	Prüfzeugnis wegungsfugen für Bau ingwiderstand gemäß Ausgabe 2014/2
Dieses algemeine bausufatte Dieses algemeine bausufatte is geten de Algemeinen Gesch Es geten de Algemeinen Gesch Dieses Diesen de Algemeinen Gesch Dieses de Algemeinen Gesch Dieses de Algemeinen Gesch Bernerstellter	An Philippengina dant nur ungebindet vervielligtig Anfehlichen Zusichnenung der MPPA Leipzig Ge- Mathebedingunen (AGB) der MPPA Leipzig Ge- Mathebedingunen (AGB) der MPPA Leipzig Ge- Mathebedingunen (AGB) der MPPA Leipzig Ge- Stehlen und Coginalitätengel desler Zusicherungs- mitten im Zusichnen (AGB) der MPPA Leipzig Ge- Mathebedingunen (GBB) der MPPA Leipzig Ge- mennen (GBB) der MPPA Leipzig Ge- Mathebedingunen (GBB) der MPPA Leipzig Ge- mennen (GBB) der MPPA Leipzig Ge- Mathebedingunen (GBB) der MPPA Leipzig Ge- mennen (GBB) der MPPA Leipzig Ge- mennen (GBB) der MPPA Leipzig Ge- mennen (GBB) der MPPA Leipzig Ge- Mathebedingunen (GBB) der Mathebedingunen (GBB) der Mathebedi	Allgemei Prützeugnis Nummer: Gegenstand: Antragsteller: Ausstellungsdatum: Geltungsdauer: Dieses aligemeine bausufski	nes bauaufsichtliches F P-SAC 02 / 5.1 / 13 - 438 Triffex JWS, Variante 2 - außaniegende Abdichtung von Be aus Boton mit hohem Wassereindt Bauregelliste A, Teil 2, lfd. Nr. 1.4, Triffex GmbH & Co. KG Karistraße 59 D 32423 Minden 12.01.2015 11.01.2020 thliche Prüfzeugnis besteht aus 9 Seiten.	Prüfzeugnis wegungsfugen für Bau ingwiderstand permäß Ausgabe 2014/2
Dieses algemeine bausuhtettei beses abereine bausuhtettei Schriftom mit Organauntenschri Es geten die Algemeinen Gesch Weiter Schriftom mit Organauntenschri Weiter Schriftom mit Organauntenschrift Weiter Schriftom mit Organauntenschrift Mitter Schriftom mit Organauntenschriftom mit Organauntenschrift Mitter Schriftom mit Organauntenschriftom mit Or	An Philipungsis darf nur ungekügt verviellikig her und Organizationnung der Läff-PA Lappig Gri her und Organizationnung der Läff-PA Lappig Gri her und Organizationnung der Läff-PA Lappig Gri her und Organizationnung der Läff-PA Lappig Gri Christigen einen einen der Kindel der Verber Leitung der her und Der Kindel der Verber Leitung der her der Schlieber einen der Kindel der Verber Leitung der her der Schlieber einen der Kindel der Verber Leitung der her der Schlieber einen der Kindel der Verber Leitung der her der Schlieber einen der Kindel der Verber Leitung der her der Schlieber einen der Kindel der Verber Leitung der Kindel her der Schlieber einen der Kindel der Verber der Kindel	Allgemein Prüfzeugnis Nummer: Gegenstand: Antragsteller: Ausstellungsdatum: Geltungsdauer: Dieses aligemeine bauaufsko	P-SAC 02 / 5.1 / 13 - 438 P-SAC 02 / 5.1 / 13 - 438 Triflex JWS, Variante 2 - außanilogande Abdichtung von Be aus Beton mit hohem Wasseneinde Bauregalitste A, Teil 2, ltd. Nr. 1.4, Triflex GmbH & Co. KG Karistraße 59 D 32423 Minden 12.01.2015 11.01.2020 httiche Prützeugnis besteht aus 9 Seiten. Prötzeugnis derf nu ungekizt vervieltigtig verden. A förfer und Orginationen deskat Zeichnungste	Prüfzeugnis wegungsfugen für Bau ingeviderstund gemäß Ausgabe 2014/2









International

Triflex GmbH & Co. KG Karlstrasse 59 32423 Minden | Germany Fon +49 571 38780-0 info@triflex.de www.triflex.de 064 Planning documents Triflex JWS EN A4 01/2016